


**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>B65H 54/52</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/61484</b> <b>(43) International Publication Date:</b> 19 October 2000 (19.10.00)																																														
<b>(21) International Application Number:</b> PCT/US00/09544 <b>(22) International Filing Date:</b> 10 April 2000 (10.04.00)  <b>(30) Priority Data:</b> 11/106859 14 April 1999 (14.04.99) JP  <b>(71) Applicant (for all designated States except US):</b> DU PONT-TORAY COMPANY, LTD. [JP/JP]; 5-6, Nihonbashi-Honcho 1-chome, Chuo-ku, Tokyo 103 (JP).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> OKADA, Tatsuyuki [JP/JP]; 16-A1-27, Takehanajizouji-minami-tyou, Yamashina-ku, Kyoto City (JP). IKETANI, Hidekazu [JP/JP]; 2-15-1-403, Sonoyama, Otsu City, Shiga (JP).  <b>(74) Agent:</b> FRANK, George, A.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> BR, CN, KR, TR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>																																														
<b>(54) Title:</b> PROCESS FOR WINDING ELASTOMERIC FIBER PACKAGE																																																
<div data-bbox="240 1276 409 1396"><b>Contact Force (kg)</b></div>  <table border="1"><caption>Data points estimated from the graph</caption><thead><tr><th>Diameter (mm)</th><th>Contact Force (kg)</th></tr></thead><tbody><tr><td>80</td><td>6.5</td></tr><tr><td>85</td><td>4.5</td></tr><tr><td>90</td><td>4.0</td></tr><tr><td>100</td><td>3.5</td></tr><tr><td>110</td><td>3.5</td></tr><tr><td>120</td><td>3.5</td></tr><tr><td>130</td><td>3.5</td></tr><tr><td>140</td><td>3.5</td></tr><tr><td>150</td><td>3.5</td></tr><tr><td>160</td><td>3.5</td></tr><tr><td>170</td><td>3.5</td></tr><tr><td>180</td><td>3.5</td></tr><tr><td>190</td><td>3.5</td></tr><tr><td>200</td><td>3.5</td></tr><tr><td>210</td><td>3.5</td></tr><tr><td>220</td><td>3.5</td></tr><tr><td>230</td><td>3.5</td></tr><tr><td>240</td><td>3.5</td></tr><tr><td>250</td><td>3.0</td></tr><tr><td>260</td><td>2.5</td></tr><tr><td>270</td><td>2.0</td></tr><tr><td>280</td><td>2.5</td></tr></tbody></table> <div data-bbox="738 1549 1031 1591"><b>Diameter (mm)</b></div>			Diameter (mm)	Contact Force (kg)	80	6.5	85	4.5	90	4.0	100	3.5	110	3.5	120	3.5	130	3.5	140	3.5	150	3.5	160	3.5	170	3.5	180	3.5	190	3.5	200	3.5	210	3.5	220	3.5	230	3.5	240	3.5	250	3.0	260	2.5	270	2.0	280	2.5
Diameter (mm)	Contact Force (kg)																																															
80	6.5																																															
85	4.5																																															
90	4.0																																															
100	3.5																																															
110	3.5																																															
120	3.5																																															
130	3.5																																															
140	3.5																																															
150	3.5																																															
160	3.5																																															
170	3.5																																															
180	3.5																																															
190	3.5																																															
200	3.5																																															
210	3.5																																															
220	3.5																																															
230	3.5																																															
240	3.5																																															
250	3.0																																															
260	2.5																																															
270	2.0																																															
280	2.5																																															
<b>(57) Abstract</b>																																																
<p>A winding process for an elastomeric fiber package, utilizing a contact roll exerting a diminishing force according to a specific profile on a tube core and on the growing package after winding begins, is provided.</p>																																																

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE OF INVENTION

## PROCESS FOR WINDING ELASTOMERIC FIBER PACKAGE

BACKGROUND OF THE INVENTION5 Field of the Invention

The present invention relates to a winding process for an elastomeric fiber package and, more particularly, to a process for winding a package utilizing a contact roll exerting variable pressure during the winding.

10 Description of Background Art

Products based on elastomeric fibers have been used in many areas such as industrial materials, clothing, and disposable personal care products (for example diapers). The elastomeric fibers have been woven and knit into  
15 fabrics, stitch-bonded into nonwovens, and directly adhered onto sheet materials such as nonwovens and films. The elastomeric fiber is ordinarily provided wound onto tubecores. The wound fiber and associated tubecore are referred to as a "package". In use, the elastomeric  
20 fiber is unwound from the package sequentially or in parallel, either passively (for example, by "over-end take-off") or actively (for example by "rolling take-off"), and fed to a downstream process.

However, there have been problems in that  
25 elastomeric fiber packages have heretofore sometimes had poor package shape. Such packages have been wound with rising force of the contact roll on the tubecore and package. This poor package shape can cause the elastomeric fiber to slough off the package readily (for  
30 example as a result of rubbing against shipping materials or other elastomeric fiber packages) so that the unwinding elastomeric fiber becomes entangled with the sloughed-off elastomeric fiber, leading to breaks in the fiber. Such breaks also occur as a direct result of the

rubbing. As a result, the economics of unwinding fibers from such packages were poor, and an improved process for winding elastomeric fiber packages is needed.

#### SUMMARY OF THE INVENTION

The process for winding an elastomeric fiber producing an inflected force profile, comprises the steps of:

(A) rotating a tubecore in contact with a contact roll;

(B) winding the fiber onto the tubecore so that the contact roll exerts an initial force against the fiber on the tubecore and a package begins to be formed;

(C) gradually reducing the force a first time during the first 30% of winding time to approximately 25-60% of the initial force;

(D) holding the force substantially constant until the final 30% of winding time; and

(E) reducing the force a second time to no less than approximately 10% of the initial force.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic side view illustrating an elastomeric fiber package obtained by the process of the invention.

Figure 2 is a plot of the force that the contact roll exerts against the tubecore and package vs package diameter from the beginning of winding to the end of winding in the process of the present invention. This is an example of an inflected force profile.

Figure 3 shows a cross-section of an elastomeric fiber package made by conventional winding.

Figure 4 illustrates an example of an uninflected force profile as used in a conventional winding process.

Figure 5 schematically illustrates an example of a means that can be used in the present process to vary the force that the contact roll exerts against the elastomeric fiber package.

#### DETAILED DESCRIPTION OF THE INVENTION

It has now been found that an elastomeric fiber package, especially a large package which has good unwinding characteristics and excellent package shape, can be made by winding the package with an inflected force profile.

"Elastomeric fiber" means a filament which has a break elongation in excess of 100% independent of any crimp and which when stretched and released, retracts quickly and forcibly to substantially its original length. Such fibers include rubber fiber, spandex or elastane, polyetherester fiber, polyetheramide fiber, certain polypropylenes, and elastoester. "Spandex" and "elastane" mean a manufactured fiber in which the fiber-forming substance is a long chain synthetic elastomer comprised of at least 85% by weight of a segmented polyurethane. "Inflected force profile" means a plot of the package diameter vs the force of the contact roll against the tubecore and winding package, the plot having a change of curvature, with respect to a fixed line, from concave to convex, or conversely, depending on the point from which the plot is viewed.

Synthetic elastomeric fibers such as elastane, polyetheramide fibers, and polyetherester fibers can be prepared from polymeric glycols; copolymeric glycols can also be used. In the case of elastane, the polymeric glycol can be a (co)polyether glycol, (co)polyester glycol, and/or (co)polycarbonate glycol. The polymeric glycol is typically reacted with a diisocyanate and at

least one diamine, alkanolamine, and/or diol to form the polymer. In the case of polyetheresters, a polyether glycol can be reacted with a diacid and at least one low-  
5 molecular weight diol to form the polymer. Polyether diamines, diacids, and low-molecular weight diamines can be used to make polyetheramides. Monofunctional chain terminators such as alcohols and amines can be used to control the molecular weight of the polymers.

10 Depending on the type of polymer to be made, solution- or melt-polymerization can be used. Correspondingly, dry-, wet-, or melt-spinning can be used to prepare the fiber, depending on the type of polymer. Additives and stabilizers can be added to the fiber,  
15 provided they do not adversely affect the process of the invention.

After the fiber has been spun, it is typically reciprocated transversely to the direction of its travel by a traverse means and wound up on a tubecore. The  
20 tubecore is customarily mounted on a spindle assembly, and the fiber is wound onto the tubecore with the aid of a contact roll. The spindle assembly can be driven and the contact roll can be undriven (freely rotating). Alternatively, the spindle assembly can be undriven, and  
25 the contact roll can be driven, thus providing the rotational drive needed to rotate the spindle assembly.

In the process of the present invention, the force exerted by the contact roll on the tube core (and after winding begins, on the growing package) is reduced during  
30 winding according to a specific profile. The force reductions are described herein by reference to the force used at the beginning of winding (the "initial force"). The maximum initial force can be 10Kg, and the minimum force can be 1 Kg. During the first 30%, preferably 10%,

of winding time, the force is gradually reduced a first time, to about 25-60% of the initial force. The contact roll force is then held substantially constant until the  
5 final 30%, preferably about 20%, of the winding time, at which point the force is reduced a second time to no less than about 10%, preferably about 10-35%, of the initial force. Winding time corresponds approximately to package diameter, and plotting the contact roll force against the  
10 diameter of the winding package gives an inflected force profile as illustrated in Figure 2.

The method of this invention provides an elastomeric fiber package which has a substantially uniform wound width, thereby providing excellent unwinding and shape  
15 retention properties. That is, the present invention produces a package as illustrated in Figure 1, which has a small difference  $\delta_w$  between the maximum value  $\delta_{max}$  and the minimum value  $\delta_{min}$  of the wound package width. A small  $\delta_w$  indicates sidewalls that are desirably  
20 substantially flat and perpendicular to the axis of the tubecore; such packages have good unwinding characteristics.

The process of the invention is especially useful for elastomeric fiber packages weighing 3kg or more and  
25 even exceeding 4kg.

Any suitable method can be used in this invention as a means to control and vary the force that the contact roll exerts against the package. For example, an apparatus as illustrated in Figure 5 can be used in which  
30 compressed air cylinder 5 operates on signals from a control device (not shown) to adjust the weight of arm 4 that supports contact roll 3 which rotates in contact with tubecore and package 1 as elastomeric fiber 2 is wound up. Thus when the cylinder is extended, the

contact roll force is reduced, and when it is contracted, the force is increased. A hydraulic cylinder can be used in place of the air cylinder. Other geometries can also be used to obtain the inflected force profile of the invention.

#### Example 1

A 560 denier (622 dtex) Lycra® spandex (Type 127; a registered trademark of E. I. du Pont de Nemours and Company) was dry-spun by conventional means and wound up on a 175-mm long tubecore to reach a wound package weight of 4.5kg. No finish was applied to the fiber. The force that the contact roll exerted against the package during winding followed the inflected force profile shown in Figure 2, in which package diameter (in mm) is plotted on the abscissa and the force that the contact roll exerts against the package (in Kg) is plotted on the ordinate. As shown in Figure 2, the total winding diameter was about 282 mm. The beginning of winding, during which the contact roll force was reduced a first time, was about 9 mm (5% of the total diameter and about 5% of the total winding time), and the end of winding during which the force was reduced a second time was about 46 mm (24% of the total diameter and about 24% of the total winding time). The force declined from about 5.7Kg at the beginning of winding to about 2.9Kg during the middle of winding, or to about 50% of the initial force. The contact roll force was held substantially constant until the end of winding, at which point it was reduced further to about 31% of the initial force, in other words to about 1.8Kg. As shown in Table 1, the difference in wound width was small and the product had excellent sidewall shape and unwinding characteristics.

Comparative Example 1

Elastomeric fiber was spun and wound up exactly as in Example 1 except that the force that the contact roll exerted against the package was increased as during conventional winding and as shown in Figure 4. As reported in Table 1, the resulting package had a wound width greater than that of the package of Example 1, showed inferior unwinding characteristics, and had an S-shape (substantial bulge) in the sidewall as illustrated in Figure 3.

TABLE 1

	Example 1	Comp. Example 1
The curve shape of the force that contact roll exerts against package	Inflected force profile, as in Figure 2	Linear, as in Figure 4
Difference in wound width $\delta_w$ (mm)	16	30
Sidewall shape	Gentle curve	S-shaped, with large bulge
Unwinding characteristics	Good	Poor

Claims:

1. A process for winding an elastomeric fiber producing an inflected force profile, comprising the  
5 steps of:

(A) rotating a tubecore in contact with a contact roll;

(B) winding the fiber onto the tubecore so that the contact roll exerts an initial force against the fiber on  
10 the tubecore and a package begins to be formed;

(C) gradually reducing the force a first time during the first 30% of winding time to approximately 25-60% of the initial force;

(D) holding the force substantially constant until  
15 the final 30% of winding time; and

(E) reducing the force a second time to no less than approximately 10% of the initial force.

2. The process of claim 1 wherein the second force  
20 reduction is to approximately 10-35% of the initial force.

3. The process of claim 1 wherein the initial force is no greater than approximately 10Kg and the final force  
25 is no less than approximately 1Kg.

4. The process of claim 3 wherein the force is reduced a first time during the first 10% of winding time and the force is reduced a second time during the final  
30 20% of winding time.

5. The process of claim 2 wherein the fiber is selected from the group consisting of spandex and

polyetherester fiber and the package size is at least about 3Kg.

- 5           6. The process of claim 3 wherein the fiber is spandex or polyetherester fiber and the package size is greater than approximately 4Kg.

1/3




FIG. 1




FIG. 2

2/3




FIG. 3




FIG. 4

3/3




FIG. 5

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/09544

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 B65H54/52

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B65H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 3 672 583 A (HARRISON ROBERT E) 27 June 1972 (1972-06-27) column 1, line 71 -column 4, line 26; figures 1,4	1-6
Y	US 2 753 125 A (A. WÜRMLI) 3 July 1956 (1956-07-03) column 2, line 1 -column 3, line 7; figures 3-5	1-6
A	US 5 727 744 A (THRELKELD JAMES O ET AL) 17 March 1998 (1998-03-17) column 3, line 43 -column 4, line 26; figure 2	5,6

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 August 2000

Date of mailing of the international search report

28/08/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 851 epo nl,  
Fax: (+31-70) 340-3018

Authorized officer

David, P

# INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 00/09544

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3672583 A	27-06-1972	NONE	
US 2753125 A	03-07-1956	BE 530982 A CH 315555 A DE 1065562 B GB 756013 A NL 87667 C	
US 5727744 A	17-03-1998	NONE	